


HK PETRO - SR550 M

High Impact Polystyrene

Property	Test method	Unit	Typical values
General properties			
Specific gravity	ASTM D792	g/cm ³	1.04
Bulk density of granules	ASTM D1895	kg/dm ³	0.65
Mechanical properties			
Izod impact strength, notched, at 23°C - 3.2mm thick specimen	ASTM D256	kgcm/cm J/m	8.5 80
Tensile properties (type I specimen, thickness 3.2mm): - yield strength - tensile strength - elongation at break - elastic modulus	ASTM D638	N/mm ² N/mm ² % N/mm ²	26 21 50 2270
Flexural properties (3.2mm thick specimen): - maximum stress - elastic modulus	ASTM D790	N/mm ² N/mm ²	48 2230
Rockwell hardness, L scale	ASTM D785		79
Thermal properties			
Heat deflection temperature (12.7mm thick specimen - 1.82 N/mm ²)	ASTM D648	°C	84
Vicat softening point, oil, speed 50 ± 5 °C/h; - 1kg load - 5kg load	ASTM D1525	°C °C	96 89
Rheological properties			
Melt flow index (condition G - 200°C, 5kg)	ASTM D1238	g/10 min	7.5

May 2003

The above data are provided for guidance purposes only. Hong Kong Petrochemical Co. Ltd. accepts no responsibility for the results obtained therefrom, as neither for their utilization in infringement of possible patent rights.



HONG KONG PETROCHEMICAL CO . LTD.

香港石油化學有限公司


HK PETRO - SR550 M

高抗衝擊聚苯乙烯

測試項目	測試方法	單位	數值
一般性能			
比重	ASTM D792	g/cm ³	1.04
堆積密度	ASTM D1895	kg/dm ³	0.65
機械性能			
懸臂樑衝擊強度	ASTM D256	kgcm/cm	8.5
- 樣本厚 0.32 公分		J/m	80
拉伸性能	ASTM D638		
(第一類樣本, 厚 0.32 公分):			
- 屈服強度		N/mm ²	26
- 拉伸強度		N/mm ²	21
- 伸長率		%	50
- 彈性模數		N/mm ²	2270
撓曲性能	ASTM D790		
(樣本厚 0.32 公分)			
- 最大壓力		N/mm ²	48
- 彈性模數		N/mm ²	2230
洛氏硬度, L 級	ASTM D785		79
熱性能			
熱變形溫度	ASTM D648	°C	84
(樣本厚 1.27 公分, 壓力 1.82 N/mm ²)			
維卡軟化點 (升溫速度 50 + 5 °C/小時)	ASTM D1525		
- 負重一公斤		°C	96
- 負重五公斤		°C	89
流動性能			
熔流指數	ASTM D1238	g/10 min	7.5
(測試條件 G - 200°C, 五公斤)			

2003年5月

上列數據乃依照所述測試方法得出之結果, 所有數據僅供作參考之用, 並非產品之規格.



HONG KONG PETROCHEMICAL CO . LTD.

香港石油化學有限公司

香港 新界元朗工業村 宏樂街十二號 電話(852) 28024860 傳真(852) 28240282

